Test Safe
AUSTRALIA

REPORT

No: 34636
Date of Issue: 26 February 2014
File No: 2013/019953

Prepared for:

BALFLEX PORTUGAL SA

FRAS Testing of DIN EN 1SN / SAE R1001AT Steel Reinforced Hose with Fire Resistant Cover to AS 2660-1991

ilac-MRA NATA

Accredited Laboratory
No. 1032

Accredited for compliance with ISO/IEC 17025. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

P O Box 592
Richmond NSW 2753
Australia

919 Londonderry Road
Londonderry NSW
Australia

Phone: 61 (0) 2 4724 4900
Fax: 61 (0) 2 4724 4999
Email: testsafe@workcover.nsw.gov.au
Website: www.testsafe.com.au

Issued by

TESTSAFE AUSTRALIA

Dealing with

FRAS TESTING OF HOSING

TO

AS 1180.10B-1982 & AS 1180.13A-1983 as referenced by

AS2660-1991

CLIENT:	Balflex Portugal SA
ADDRESS:	Rua Bouca Estilhadouros, N226/254 – Zona Industrial Alto Vilar – 4445-044 Alfena – PORTUGAL
DATE OF APPLICATION:	29 November 2013
TESTSAFE JOB No:	M16972
PRODUCT:	Hydraulic hose
SAMPLE DESCRIPTION:	Steel Reinforced Hose with Fire Resistant Cover DIN EN 1SN / SAE 100R1AT
APPLICATION:	Hydraulic Equipment
MANUFACTURER:	Balflex Portugal – Componentes Hidraulicos E Industriais, S.A.
NOMINAL DIMENSIONS:	27.8mm O.D x 19.0mm I.D
HOSE ITEM NUMBER:	10.1002.12
COLOUR & LABELLING:	Black with White & Blue
TEST SPECIFICATION:	AS 1180.10B-1982 AS 1180.13A-1983 Acceptance Criteria as given in Clauses 2.1 and 2.2 of AS 2660-1991 *Fire resistant and antistatic requirements for conveyor belting used in underground coal mines*
OVERALL RESULT:	Pass

1. TEST EQUIPMENT

- Flame Test Apparatus
- Tape Measure, Craftech, TS-5
- Stop Watch, Hart Sport, s/no. Mech Stop 2
- Temperature/Humidity Indicator, TSI, s/no. 97040434
- Resistance Bridge, Megger, s/no. 000713
- Vernier, Mitutoyo, s/no. 0025652

2. TEST RESULTS

2.1 Test to AS1180.13A-1983

Test Date: 16/01/2014

Sample Length: 1050 mm

Surface Measurement:
Ambient Temperature: 22.7 °C
Relative Humidity: 51.8 %

TEST DATA:

Outer Surface

Sample Number	Surface Resistance (MΩ/m)
S8867ER-1	0.027
S8867ER-2	0.029
Total	0.056
Average	0.028

Inner Surface

Sample Number	Surface Resistance (MΩ/m)
S8867ER-1	0.002
S8867ER-2	0.002
Total	0.004
Average	0.002

Acceptance Criteria: AS2660-1991 Clause 2.2:

'When hose is tested in accordance with 1180.13A, using the flexible ring electrodes for the external surface and the plug electrodes for the internal surface, the electrical resistance shall not be greater than 1 MΩ/m'

RESULTS: Pass

COMMENTS: Nil

2.2 Tests to AS1180.10B-1982

Test Date: 22/01/2014

Sample Length: 300 mm

TEST DATA:

Sample Number	Duration of Flame (sec)	Duration of Glowing (sec)	Maximum Charred Length (mm)
S8867F-1	0	0	52
S8867F-2	1	0	57
S8867F-3	0	0	53
S8867F-4	1	0	46
S8867F-5	0	0	50
S8867F-6	0	0	52
Total	2	0	310
Average	0.3	0	51.7

Acceptance Criteria: AS2660-1991 Clause 2.1:

'When hose is tested in accordance with 1180.10B, the average duration of flaming and glowing shall not exceed 30 s'

RESULTS: Pass

COMMENTS:

1. AS 1180.10B requires charred length to be recorded, therefore, the maximum charred lengths have been included in this report.

2. AS2660 Clause 2.1 requires only the flame and afterglow duration to be used as criteria for pass/fail.

Signatory: _____
(L.Gerisch)



Photo of Sample DIN EN 1SN / SAE 100R1AT